

Tecnical data sheet

Temporary protection film

R0412

Surface protetion film

| | |
|---------------|---------------------|
| Film Carrier | LDPE high tech |
| Colour | Clear / Transparent |
| Adhesive Type | Rubber based |

Technical Specification

| <i>Properties</i> | <i>Unit</i> | <i>Value</i> | <i>Test method</i> |
|----------------------|-------------|--------------|--------------------|
| Total Thickness | µm | 72 ± 6 | AFERA 4006 |
| Tensile Strength MD | N/inch | > 26 | AFERA 4004 |
| Tensile Strength TD | N/inch | > 18 | AFERA 4004 |
| Elongation MD | % | > 200 | AFERA 4005 |
| Elongation TD | % | > 400 | AFERA 4005 |
| Adhesion to BA steel | cN/cm | 80 ± 20 | AFERA 4001 |



APPLICATION

SOPRAD protection film is mainly used for the protection against mechanical damage, dirt, scratch, abrasion during storage, transportation and light manufacturing.
SOPRAD surface protection film are not to be used for permanent protection, they should be removed as soon as possible and in any case immediately at the end of the supply chain.
The product is specially designed to protect the following surfaces:

- Varnished Surfaces
- Powder Coated Metallic Surfaces
- Highgrade Steel
- Stainless Steel

The product is not suitable for copper and brass.

LAMINATION

The surfaces must be free from any oil, dust and solvents, the surface must be dry .
SOPRAD recommend to apply the product under a room temperature between 15°C and 40°C.
SOPRAD protection film must be applied by the use of an automatic mechanical machineries in order to avoid bubbles and wrinkles formation. Excessive tension during lamination must be avoid (max 1%).
This product must be removed within 6 months from lamination date.
The product is designed to resist 6 months on outside exposure under standard conditions.
Soprad recommend to verify that during sunlight and moisture exposure the protected surface is not subject to any variation on its characteristic (i.e. gloss,colour,etc.)

PRESENTATION

SOPRAD protective film is generally supplied in rolls with a length that may vary from 500 mtl to 2000 mtl in a max. width of 2320 mm.
Packaging could be customized according customer request
Internal roll diameter.....76mm
External roll diameter.....450mm

STORAGE AND USAGE

The SOPRAD product must be stored in its original packaging, in a clean and dry conditions inside a closed warehouse.
Lamination must be done within six (6) months from delivery date.

GENERAL GUARANTEE CONDITIONS AND LIABILITY

SOPRAD protection film are designed for temporary protection of surfaces against mechanical damage, dirt, scratch, abrasion during storage, transportation and light manufacturing.
SOPRAD protection film are not meant to be used for protection against corrosion, humidity and chemicals agents.
Performances of SOPRAD protection film might be affected by various elements such as surfaces compositions of the substrate, presence of impurity and ambient conditions, for this reason SOPRAD strongly recommend and ask to customers to check the product and run a complete internal test before to use it.
During customer evaluation test the type of surface, way of applications and process condition must be considered.
The principal mentioned in this technical data sheet are only indicative, customer are fully responsible for the way of usage, SOPRAD can not in any case be engaged for any damage caused by a wrong utilization.
SOPRAD's liability shall be limited to a replacement, a reimbursement and/or to an additional delivery of the product and shall not exceed the purchase value of the product.

